



APPLICATION GUIDE

POLYURETHANE SYSTEMS
COMPACT


**SOLVENT
FREE**



Perfection and style become creative art

Ease of use, ease of implementation, excellent accuracy of the details.
It combines simplicity of use to high production capacity
for very complex shapes.



POZZI INDUSTRIES
MADE IN ITALY

OPERATING INSTRUCTIONS

1



WEIGHING



Weigh the two components separately in the indicate ratio. Use the system a 25°C temperature maximum.

2



MIXING



Combine the components and mix them for 20 seconds to obtain a homogenised blend.

3



POURING



Pour the product in the silicon rubber mold.

4



DEMOLDING



After 5 minutes remove the pieces from the mold.

- Keep the system away from moisture